104.2 Royal Canadian Mint Reference Materials (solid forms)

These RMs are a series each of fine gold and gold bullion products developed and certified by the Royal Canadian Mint (RC The fine gold RMs are primarily intended for use as calibration standards for the determination of trace elements by solid sample spectrometric methods; the RMs are primarily intended for use as quality control check standards for fire assay. There are five RMs in the gold bullion series, and six RMs in the fine gold series. The RMs in the gold bullion series are available in three forms disc (25 mm dia. x 20 mm), wire (2 mm dia.), and foil (35 mm x 40 mm x 1 mm). The RMs in the fare available in three formsblock (25 mm x 25 mm), wire (2 mm dia.), and turnings (25 g).

PLEASE NOTE: The tables are presented to facilitate comparisons among a family of materials to help customers select the best SRM for their needs. For specific values and uncertainties, the certificate is the only official source.

RM Description		68/8069/807 Gold Bullion	0		71/8072/807 Gold Bullion)74/8075/807 Gold Bullion	6		77/8078/807 Gold Bullion			80/8081/808 Gold Bullion	
Form	D	W	F	D	W	F	D	W	F	D	W	F	D	W	1
(Disc, Wire, Foil) Unit Size (in g)	30	25	25	30	25	25	30	25	25	30	25	25	30	25	2
						Comp	onents (mg/	′kg)							
Au		94.847			89.928			84.905			79.962			74.988	
Ag		4.15			8.03			12.08			15.09			15.04	
Cu		(1)			(2)			(3)			(5)			(10)	

RM	805	0/8051/8	052	805	3/8054/8	055	805	6/8057/8	8058	805	9/8060/8	3061	806	2/8063/8	8064	80	65/8066/8	067	
Description	F	Fine Gold	d	F	Fine Gol	d	F	Fine Gol	d	F	ine Gol	d	F	ine Gol	d		Fine Gol	d	
Form	В	W	Т	В	W	Т	В	W	Т	В	W	Т	В	W	Т	В	W	Т	
(Block, Wire,	30	25	25	30	25	25	30	25	25	30	25	25	30	25	25	30	25	25	
Turnings)																			
Unit Size (in a)																			

			Components (mg/	kg)		
Λ.	0.4	10.0	10.0	0.7	00.4	14.0
As	2.4	10.0	18.0	6.7	29.4	14.3
Bi	3.4	24.0	34.0	6.8	53.9	11.0
Cr	1.7	32.6	13.3	5.0	4.9	16.7
Cu	1.6	98.1	46.9	5.7	9.8	13.8
Fe	6.2	11.6	33.8	7.5	90.4	15.4
Pb	1.9	21.9	30.5	6.4	49.7	11.5
Иg	1.1	34.0	11.8	6.0	3.2	15.6
Иn	1.1	58.9	22.5	10.8	64.3	20.5
Ni	2.7	32.5	50.5	5.7	14.6	13.5
Pd	1.3	43.1	19.8	5.0	119	13.1
Pt		87.1	40.8	6.1	5.1	12.5
Si		2.7	27.8	6.3	9.0	19.1
Ag	9.5	20.3	81.7	7.1	49.7	15.1
Sn	2.8	33.8	27.2	6.4	49.7	17.8
Ti	0.7	12.7	25.3	5.9	2.6	16.5
Zn	2.6	54.6	6.6	7.5	20.9	12.5

Values in parentheses are not certified and are given for information only.